




DE92010947

NTIS
Information is our business.

IMPROVED FISCHER-TROPSCH CATALYSTS FOR INDIRECT COAL LIQUEFACTION. FINAL REPORT

SRI INTERNATIONAL
MENLO PARK, CA

FEB 1989



U.S. DEPARTMENT OF COMMERCE
National Technical Information Service

SRI International



DOE/PC/80016-T10
(DE92010947)
Distribution Category UC-108

IMPROVED FISCHER-TROPSCH CATALYSTS FOR INDIRECT COAL LIQUEFACTION

February 1989

Final Report

By: R. B. Wilson Jr., G. T. Tong, Y. W. Chan, H. W. Huang,
and J. G. McCarty

Prepared for:

UNITED STATES DEPARTMENT OF ENERGY
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, Pennsylvania

Attn: Mr. Edgar B. Klunder

Contract No. DE-AC22-85PC80016

SRI Project PYU 1245

Approved by:

D. D. Macdonald, Laboratory Director
Materials Research Laboratory

G. R. Abrahamson
Senior Vice President
Sciences Group

CONTENTS

	<u>Page</u>
EXECUTIVE SUMMARY.....	1
I CLUSTER-DERIVED FTS CATALYSTS.....	I-1
Introduction.....	I-1
Background.....	I-5
Strategy for Selection of Non-ASF FTS Catalysts.....	I-5
Review of Synthesis Methods.....	I-12
Experimental Results.....	I-14
Synthesis.....	I-14
Subtask 1: Synthesis of Hydridocarbonyl Ruthenium Clusters.....	I-15
Subtask 2: Reaction of Hydridocarbonyl Ruthenium Clusters with Alkyl Aluminum.....	I-16
Subtask 3: Reaction of Alkyl Aluminum Carbonyl Ruthenium Clusters with the Support.....	I-17
Subtask 4: Synthesis of Alkyl Complexes of Ruthenium..	I-19
Subtask 5: Reaction of Alkyl Complexes of Ruthenium with the Support.....	I-20
Characterization.....	I-20
Catalysis.....	I-25
Fixed-Bed Reactor.....	I-25
Slurry Phase.....	I-27
Discussion.....	I-27
References.....	I-31
II SULFUR TREATED CATALYSTS.....	II-1
Introduction.....	II-1
Background.....	II-3
Selective Poisoning of FTS Catalysts.....	II-3
Uniform Sulfur Adsorption on FTS Catalysts.....	II-4
Experimental Results.....	II-5
Catalyst Preparation.....	II-5
Sulfur Treatment of Precipitated Iron Catalysts.....	II-7
Sulfur Treatment of Fused Iron Catalysts.....	II-9
Sulfur Treatment of Cobalt Catalysts.....	II-12
Characterization and Testing of FTS Catalysts.....	II-14
Experimental Procedures.....	II-14
FTS Testing of Clean and Sulfur-Treated Fused Iron Catalysts.....	II-16
FTS Testing of Clean and Sulfur-Treated Cobalt Catalysts.....	II-25
Clean and Sulfur-Treated Precipitated Iron Catalysts.....	II-30
Evaluation of Improved FTS Catalysts.....	II-30
Discussion.....	II-35
Recommendations.....	II-39
References.....	II-41

CONTENTS (continued)

	<u>Page</u>
III SYNTHESIS OF AROMATIC HYDROCARBONS.....	III-1
Introduction.....	III-1
Background.....	III-2
Direct Synthesis of Aromatic Hydrocarbons.....	III-2
Effect of Promoters of FTS Catalysis.....	III-4
Carbon Deposition.....	III-6
Experimental Results.....	III-7
Sulfur Treatment of FTS Catalysts.....	III-7
Medium-level Sulfur Treatment of Ru/Al ₂ O ₃ Catalysts.....	III-7
Discussion.....	III-11
Conclusions and Recommendations.....	III-17
References.....	III-18

LIST OF FIGURES

	<u>Page</u>
I-1. Comparison of ASF and Poisson Distribution for the Same Average Degree of Polymerization $P_n = 10$	I-4
I-2. Effect of Average Degree of Polymerization (P_n) on the Product Mix for FTS with an ASF Distribution.....	I-6
I-3. Operating Regimes for FTS Catalysts	I-7
I-4. Comparison of the Product Distribution Obtained by Madon over 1% Ru/Al ₂ O ₃ at 241°C, 30 atm, and H ₂ /CO = 2 with the ASF Theoretical Distribution.....	I-9
I-5. Diffuse Reflectance FTIR Spectra for Alumina-supported Ruthenium Hexameric Carbonyl Cluster Catalyst Before Activation.....	I-21
I-6. Temperature-Programmed Desorption of Mass 28 for Surface-confined Ruthenium Hexamer Cluster Catalyst.....	I-22
I-7. Diffuse Reflectance FTIR Spectra for Alumina-supported Ruthenium Hexameric Carbonyl Cluster Catalyst After TPD.....	I-24
I-8. Catalyst Characterization and Testing Apparatus.....	I-26
II-1 FTS Catalyst Sulfur Treatment System.....	II-8
II-2 Sulfur Chemisorption Isotherms on Fused Iron and Iron Powder.....	II-10
II-3. Sulfur Chemisorption Isotherms on Cobalt/Al ₂ O ₃ and Cobalt Powder.....	II-13
II-4. Catalyst Characterization and FTS Testing Apparatus.....	II-15

LIST OF FIGURES (continued)

	<u>Page</u>
II-5. Schulz-Flory Plot of the Hydrocarbon Product Distribution for Clean and Sulfur-Treated Fused Iron Catalysts at 573 K, 100 kPa, and $H_2/CO = 1.0$	II-19
II-6. Fischer-Tropsch Synthesis at 573 K, 100 kPa, and H_2/CO ratio = 1, on Clean and Low-level Sulfur-treated Fused Iron Catalysts after 22 h.....	II-21
II-7. Fischer-Tropsch Synthesis at 573 K, 100 kPa, and H_2/CO ratio = 1, on Clean and Medium-level Sulfur-treated Fused Iron Catalysts after 24 h.....	II-22
II-8. Fischer-Tropsch Synthesis at 573 K, 100 kPa, and H_2/CO ratio = 1, on Clean and High-level Sulfur-treated Fused Iron Catalysts after 24 h.....	II-23
II-9. Fischer-Tropsch Synthesis at 573 K, and 100 kPa on Fused Iron Catalysts.....	II-24
II-10 Effect of Sulfur Treatment on Light Hydrocarbon Product Rate During Fischer-Tropsch Synthesis at 573 K and 100 kPa on Fused Iron Catalysts.....	II-26
II-11 Schultz-Flory Plot of the Hydrocarbon Product Distribution for Cobalt on Alumina Catalyst at 100 kPa and $H_2/CO = 1.0$	II-28
II-12 Fischer-Tropsch Synthesis at 100 kPa and H_2/CO Ratio = 1.0 on Clean Fused Iron and Clean Cobalt Catalysts at 573 K and 548 K, Respectively.....	II-29
II-13 Schulz-Flory-Anderson Plot of the Hydrocarbon Product Distribution for Fused Clean Iron, Medium-level Sulfur-treated Iron, and Medium-level Sulfur-treated Cobalt Catalysts at 2 MPa, $H_2/CO = 1$, and 573 K and 523 K, Respectively.....	II-32
II-14 Chain Growth Probability Factor for Clean and Sulfur-treated Fused Iron Catalysts with H_2/CO Ratio = 1.0.....	II-33
II-15. Methane Selectivity for Fixed-bed FTS by Clean and Sulfur-treated Fused Iron Catalysts with H_2/CO Ratio = 1.0.....	II-37
II-16 Light Olefin Selectivity for Fixed-bed FTS by Clean and Sulfur-treated Fused Iron Catalysts with H_2/CO Ratio = 1.0.....	II-38
III-1 Aromatic Synthesis at 2 MPa, 650 K, H_2/CO Ratio = 1.0, on Medium-level Sulfur-treated Fused Iron Catalyst and LZY-52 Zeolite.....	III-10

LIST OF FIGURES (continued)

	<u>Page</u>
III-2 Aromatic Synthesis at 2 MPa, 573 K, H ₂ /CO Ratio = 0.5, on Mixed Medium-level Sulfur-treated Fused Iron and Na-Y Zeolite Catalysts	III-12
III-3 Aromatic Synthesis at 2 MPa, 573 K, H ₂ /CO Ratio = 0.5, on Medium-level Sulfur-treated Fused Iron Catalyst and Na-Y Zeolites.....	III-13
III-4 Effect of Temperature on the Synthesis of Oxygenates and Aromatics at 2 MPa and H ₂ /CO Ratio = 0.5 on Medium-level Sulfur-treated Fused Iron Catalyst and LZY-52 Zeolite.....	III-16

LIST OF TABLES

I-1. Comparison of FTS and Ziegler-Natta Reactions.....	I-2
I-2. Leith's Data for Ru-Y Catalyzed FTS.....	I-12
I-3. FTIR and NMR Spectra of Ruthenium Hydridocarbonyl Clusters.....	I-18
I-4. Elemental Analysis of Ruthenium Cluster Catalysts Supported on λ -Alumina.....	I-19
I-5. He TPD of Ruthenium Cluster Catalysts at 5°/min Up to 300°C.....	I-23
I-6. FTS Performance of Ruthenium Cluster and Conventional Ruthenium Catalysts.....	I-28
I-7. Results of Slurry Reactor FTS Experiments.....	I-29
II-1. Sulfur Chemisorption Thermodynamics for Iron, Cobalt, and Ruthenium.....	II-6
II-2. Experimental Parameters for FTS Catalyst Evaluation.....	II-17
II-3. Fixed-Bed FTS Performance of Clean and Sulfur-treated Fused Iron at 1-atm.....	II-18
II-4. Fixed-Bed FTS Performance of Clean Fused Iron and Clean and Sulfur-treated Cobalt Catalysts.....	II-27
II-5. Fixed-Bed FTS Performance of Clean and Sulfur-treated Fused Iron Catalysts at 20-atm.....	II-31
II-6. FIMS Analysis of FTS Wax.....	II-34
III-1. Synthesis of Aromatics and Oxygenates by Mixtures of Sulfur- treated Fused Iron and Zeolite Catalysts.....	III-9
III-2. Synthesis of Aromatics and Oxygenates by Mixtures of Sulfur- treated Ruthenium and Zeolite Catalysts.....	III-14