

30/HBG-22

ERNST SCHLIEMANN'S EXPORT-CERESIN-FABRIK

PARIS 1900 GR. PREIS

RG-Nr. 0/0496/0799

To
British-American Commission,
Shell House,
Hamburg.

000325

Sammel-Nr. 34 17 41

24. HAMBURG 36.

Ihre Zeichen

Ihre Nachricht vom

Meldungsapparat

Meine Zeichen

Alsterufer 4-5

02

wr/th October 11th, 1945.

Betreff

Answering questions regarding Waxes:

- (1) No waxes are produced from petroleum, brown coal oils, and no Fischer Tropsch processes are being applied.
- (2) No candle manufacture, paper impregnation or insulating work is done at my works.
- (3) Slack waxes are bleached by means of bleaching earth or refined with sulphuric acid or aluminum chloride.
- (4) No grease is manufactured.
- (5) Micro - crystalline waxes such as petrolatum and ozokerite are bleached and refined as under (3).
- (6) No grease is manufactured.
- (7) Bleaching with bleaching earth gives net yields of about 92% of bleached material.

Refining with aluminum chloride gives yields between 70 to 78% of refined wax.

Yields from refining by sulphuric acid vary between 48 to 92% according to nature of crude wax.

Special wax compounds for many technical uses are made from refined waxes by ordinary melting processes.

ppa. Ernst Schliemann's Export-Ceresin-Fabrik