

PATENT SPECIFICATION

654,492



Date of Application and filing Complete Specification July 26, 1948.

No. 15917/48.

Application made in United States of America on Aug. 5, 1947.

Complete Specification Published June 29, 1951.

3501

Index at acceptance:—Classes 1(i), F3b1; and 2(iii), B1g.

COMPLETE SPECIFICATION

Hydrocarbon Synthesis

We, STANDARD OIL DEVELOPMENT COMPANY, a Corporation duly organised and existing under the Laws of the State of Delaware, United States of America, 5 having an office at Elizabeth, New Jersey, United States of America, do hereby declare the nature of this invention and in what manner the same is to be performed, to be particularly described and ascertained in and 10 by the following statement:—

The present invention relates to a catalytic process for synthesizing hydrocarbons and oxygenated hydrocarbons 15 from hydrogen and the oxides of carbon. In particular, this invention relates to carrying out the foregoing synthesis in the presence of a fluidized bed of powdered iron catalyst under conditions 20 such that good yields of desired products are obtained and at the same time disintegration and fragmentation of the powdered iron catalyst, comprising a fluidized bed thereof, is materially 25 reduced.

At the present time, considerable research is being conducted in the field of hydrocarbon synthesis employing fluid catalyst technique. The catalyst is iron 30 containing promotional amounts of known activators such as K_2O , KF , and others. The reaction between the hydrogen and the oxides of carbon is one which results in catalyst disintegration or fragmentation due to the deposition of 35 carbon in some form thereon. The powdered iron should not contain a preponderance of catalyst particle fines, and, in fact, should not contain more than about 20% of catalyst having a particle size from 0 to 20 microns, since a 40 materially greater quantity of fines than that indicated renders the catalyst non-adaptable for good fluidization. It can thus be seen that the physical disintegration of the catalyst is a highly undesirable 45 result.

In brief compass, the present improvements involve retarding or delaying the

deposition of carbonaceous material on 50 the catalyst and thereby retarding or delaying its physical disintegration, by first pretreating the catalyst, in the reaction zone or outside it, with a feed gas containing relatively large quantities of 55 hydrogen with respect to the carbon monoxide, and thereafter reducing the ratio of hydrogen to carbon monoxide when the catalyst has acquired resistance to fragmentation. During the pre- 60 conditioning of the catalyst with a synthesis gas containing a relatively high ratio of hydrogen to carbon monoxide, even though the process is operated under synthesis conditions of temperature, 65 pressure and contact time, the yields are relatively low; but after the aforesaid preconditioning treatment of the catalyst has been accomplished, the yields of 70 desired materials, such as normally liquid hydrocarbons and oxygenated hydrocarbons, is increased to a satisfactory level by reducing the ratio of hydrogen to carbon monoxide in the synthesis gas. During the preconditioning 75 period a high hydrogen partial pressure is maintained in the reaction zone, but this is lowered by lowering the ratio of hydrogen to carbon monoxide in the fresh feed in order to obtain high yields 80 after the preconditioning period is over.

The main object of the present invention, therefore, is to operate a hydrocarbon synthesis process employing the fluid catalyst technique under such con- 85 ditions that fragmentation of the catalyst is repressed.

Other and further objects of the invention will appear hereinafter.

Before setting forth a detailed description of the several runs which were 90 made in connection with the present invention, it is deemed advisable to define some of the terms to be used in connection with the said description. 95

In the first place, by "fluid catalyst technique" is meant that type of operation in which a gasiform material is

[Price 2/-]

caused to flow upwardly in the catalyst zone containing a powdered catalytic material at such a flow rate that the catalyst in powdered form is maintained in the form of a dense, ebullient turbulent suspension.

As hereinafter used, the term "synthesis gas" refers to the fresh feed gas to the reaction zone, and the most important constituents thereof are hydrogen and carbon monoxide, although it may contain minor amounts of normally gaseous hydrocarbons, some water and even some nitrogen. In operating this process, it has been found that it should contain only a small amount of carbon dioxide, preferably 2% or less.

In the accompanying drawing, there is shown diagrammatically, an apparatus in which a preferred modification of this invention may be carried into effect.

Referring in detail to the drawing (1) represents a reactor provided as shown with a grid or screen (2) and containing a body of powdered iron catalyst (3) in the form of a fluidized mass or bed. Synthesis gas enters the system through line (4) and is discharged into the bottom of reactor (1) where it passes upwardly at a sufficiently low superficial velocity to form the dense, fluidized mass previously referred to. This fluidized mass or bed will have an upper dense phase level at some point (1'), depending upon the superficial gas velocity and the actual weight or amount of catalyst in the reactor. Preferably there is a substantial distance between the upper dense phase level (1') and the top of the reactor in which the more dilute phase of catalyst exists and which in effect operates as a catalyst disengaging space, for it is the purpose of so operating such a process as to effect a separation of the main bulk of catalyst from the reactor before the crude reaction products or vapors exit from the said reactor. To effect a further separation of catalyst from vapors passing out of the reactor, it is good practice to dispose in the top of the reactor a plurality of solids separating devices (4) which may be, for example, centrifugal separators through which the vapors or gases are forced for the purpose of separating additional quantities of entrained catalyst and returning them through dip-pipes to the dense phase level. The product vapors are then withdrawn through line (5), discharged usually into a cooler (6), where they are cooled below the condensation temperature of water and then withdrawn through line (7) and discharged into a product purification and recovery system (8) wherein desired products such

as gasoline, gas oil, various oxygenated compounds and the like, may be subjected to fractional distillation and recovered according to known procedure. It should be pointed out, of course, that the process results in the production of water and oxygenated compounds which are soluble in the water. There are other oxygenated compounds which are soluble in, or associated with, the oil, but the recovery of these oxygenated hydrocarbons may be accomplished according to known means, and since the present improvements do not go to that phase of the operation, it will not be necessary to describe such product recovery in detail herein.

Referring again to the recovery apparatus (8), at least a portion of the uncondensed gases are recycled via line (9) to line (4) for further use in the process. In other words, the gases in line (9) may, and usually do, contain some unconverted hydrogen and carbon monoxide. It is of course, desirable to return this material for economical reasons to the reactor to secure complete conversion of unreacted material. The recycle gas will also contain normally gaseous hydrocarbons.

Set forth below are several runs which were made, or rather several phases of the same general run, in order to test the utility of this invention. In these runs a synthetic ammonia catalyst (dused magnetite) promoted with 0.7 weight per cent. of potassium carbonate reported as K_2O was employed. During the various periods or phases of the run which are about to be described, the temperature was maintained at about 650° F. and a total pressure of 400 pounds/sq. inch was maintained in the reaction zone. During the periods, a "superficial" gas velocity of about 0.5 feet per second was maintained in the reaction zone in all but one of the periods.

PERIOD A.

During this period, which covered a period of 198 hours, the fresh feed gas, the gas in line (2), had a hydrogen to carbon monoxide ratio of 3.1 to 1, whereas the total feed had a hydrogen to carbon monoxide ratio which varied during the run from 6 to 10 mols of hydrogen per mol of carbon monoxide. The recycle ratio, that is, the ratio of the volumes of gas fed to the reactor from line (9), compared with those entering through fresh feed line (2), was 2 to 1. In other words, for every 2 volumes of gas entering the reactor, 2 of these volumes was material recycled through line (9). The hydrogen partial pressure of the gas entering the reactor was 273

pounds absolute. During Period A, 0.21 grams of carbon was formed on the catalyst per cubic meter of carbon monoxide and hydrogen consumed. At the end of this period a representative sample of the catalyst was removed from the reactor and it was found that it contained 5.3 weight per cent. carbon based on the catalyst, that the density of the catalyst was virtually unchanged, the fresh catalyst charged to the reactor having a density of 2.4 grams per cc., while that removed at the end of the period had a density of 2.35. There was, therefore, no expansion of the catalyst, and the upper dense phase level (corresponding to (L) in the drawing) did not rise, indicating that there was virtually no fragmentation of the catalyst, that the iron catalyst remained in a well-fluidized condition and that the process operated satisfactorily. While the yields of desired product were low, namely 119 cubic centimeters of C_4+ hydrocarbons per cubic meter of hydrogen and carbon monoxide converted, nevertheless the process was deemed to have operated satisfactorily during this initial stage, for the purpose was to condition the catalyst so as to make it resistant to physical disintegration and the formation of substantial quantities of fines.

PERIOD B.

In this period, the same recycle ratio was employed as in Period A, and furthermore, the same conditions of temperature and pressure were maintained in the reaction zone. The ratio of hydrogen to carbon monoxide in the fresh feed was 2.6 mols of hydrogen per mol of carbon monoxide and from 5 to 6.6 mols of hydrogen per mol of carbon monoxide were maintained in the total feed in this period. A hydrogen partial pressure of 226 pounds absolute prevailed at the point where the gases entered the reactor. The length of this period was 176 hours. It was noted that the production of carbonaceous material on the catalyst was even lower in this period than in Period A, for analysis showed that 0.11 grams of carbon per cubic meter of carbon monoxide and hydrogen consumed were formed on the catalyst. It was also noted that there was virtually no expansion of the fluid catalyst bed, that is to say, the upper dense phase level did not rise, and that a sample of the catalyst withdrawn from the reactor at the end of the run had a density of 2.37 grams per cubic centimeter. Analysis showed that the catalyst contained 8 weight per cent. carbonaceous material based on the catalyst.

The yields during this period show an improvement, namely 29 cubic centimeters of C_4+ hydrocarbons and oxygenated hydrocarbons (exclusive of water phase) were obtained.

PERIOD C.

In this period, the same recycle ratio, namely 2:1, was employed, the temperature and pressure were also the same as in Periods A and B. But in this run the molecular ratio of hydrogen to carbon monoxide was reduced, the fresh feed having a ratio of 2.1 mols of hydrogen per mol of carbon monoxide, whereas the total feed had from 3.7 to 4.3 mols of hydrogen. The hydrogen partial pressure during this period was somewhat lower, being 187 pounds per square inch absolute. During this period, 0.16 grams of carbon per cubic meter of carbon monoxide and hydrogen converted were formed on the catalyst. A yield of 174 cubic centimeters of C_4+ hydrocarbons and oxygenated hydrocarbons (exclusive of water phase) were formed during this period, which extended for 244 hours. During this period, there was a 30% expansion in the depth of the bed, that is to say, the upper dense phase level rose to that extent. An analysis of the catalyst showed that it contained 13.3 weight per cent. carbon based on the catalyst and that its density was 1.9.

PERIOD D.

In Period D, the same recycle ratio, same temperature, same pressure and virtually the same superficial gas velocity in the reactor were maintained as in the prior periods, but here the hydrogen to carbon monoxide ratio in the fresh feed was reduced to 1.9 mols of hydrogen per mol of carbon monoxide; and in the total feed, from 3 to 3.5 mols of hydrogen per mol of carbon monoxide were present. The hydrogen partial pressure was 170 pounds per square inch absolute. During this period, which extended for 203 hours, 0.24 grams of carbon per cubic meter of carbon monoxide and hydrogen consumed were formed on the catalyst. The yield was 178 cubic centimeters of C_4+ hydrocarbons per cubic meter of carbon monoxide and hydrogen consumed. A sample removed at the end of the run from the reactor and analyzed showed that the same contained 23.9 weight per cent. of carbonaceous material on catalyst, that the density of the catalyst as removed was 1.4 grams per cubic centimeter. During this period, the dense phase suspension or fluidized bed expanded 50%.

PERIOD E.

In Period E, the same recycle ratio, same temperature, same pressure and virtually the same superficial gas velocity in the reactor were maintained as in the prior periods, but here the hydrogen in the fresh feed was 1.5 moles of hydrogen per mole of carbon monoxide; and in the total feed from 2.1 to 2.3 volumes of hydrogen per volume of carbon monoxide. The hydrogen partial pressure during this period was 129 pounds per square inch. During this period, which extended through 210 hours, 0.28 grams of carbon per cubic meter of hydrogen and carbon monoxide consumed were laid down on the catalyst. The yield was 188 cc. of C_4 + hydrocarbons per cubic meter of hydrogen and carbon monoxide consumed. At the expiration of this period, the catalyst contained 42 weight per cent. carbonaceous material, that is to say, carbon in an extractable form, carbon in the form of iron carbide, and carbon which was neither extractable nor in the form of iron carbide.

PERIOD F.

In this period, the same conditions of temperature and pressure were employed as in the previous periods, but the recycle ratio was increased up to 6 volumes of recycle material per volume of fresh feed. The hydrogen in the fresh feed had a mole ratio of 2:1 with respect to the carbon monoxide; and the total feed, from 3 to 3.3:1. In this period, the hydrogen partial pressure was 15 pounds. The space velocity was somewhat lower here, also being of the order of 0.38 feet per second expressed as superficial velocity. During the run, 1.4 grams of carbon was formed per cubic meter of hydrogen and carbon monoxide consumed. The yield was 183 cubic centimeters of C_4 + hydrocarbons. The duration of this period was 138 hours. During this time, the expansion of the dense phase suspension or bed was 66%.

In order to demonstrate the improvement attainable by preconditioning the catalyst, consider the run made below under the conditions set forth below, comparable to Period E, except that the catalyst was not preconditioned, as follows:—

Operating with 1.91 H_2/CO in the fresh feed, 7/1 recycle ratio, and 74 psig. hydrogen partial pressure, the yields of

C_4 + hydrocarbons and carbon were 188 cc. C_4 + hydrocarbons per cubic meter H_2 + CO consumed, and 7.5 grams carbon per cubic meter H_2 + CO consumed. It will be noted that more carbon accumulated on the catalyst that had not been preconditioned (compare 7.5 grams carbon per cubic meter H_2 + CO consumed). In other words, a catalyst that has been preconditioned can be used at the typically severe conditions of a hydrocarbon synthesis reaction with less carbon formation than one which has not been so conditioned.

It will be noted that in the immediately preceding run, carbon formation was 7.5 grams per cubic meter of H_2 + CO consumed, whereas in Period E, the carbon formation on the same basis was merely 1.4. In other words, the preconditioning of the catalyst as indicated in Period E, very definitely decreases rate of carbon formation on the catalyst.

The results of the runs indicate that the hydrocarbon synthesis process may be improved by subjecting the catalyst to a preconditioning treatment with synthesis gases under synthesizing conditions, the synthesis gas, however, containing a relatively large proportion of hydrogen with respect to carbon monoxide. This proportion should be at least 2.5 and preferably more than 3 moles of hydrogen per mole of carbon monoxide. Between 3.5 and 10 moles of hydrogen per mole of carbon monoxide is particularly preferred. The preconditioning period should extend from 10 to 300 hours, preferably from 40 to 200 hours, during which preconditioning period relatively low yields of desired products may be expected. Following the preconditioning period the ratio of hydrogen to carbon monoxide in the total feed may be reduced to the order of 2 moles of hydrogen per mole of carbon monoxide or lower, and in this manner the yields of desirable products such as C_4 + hydrocarbons will be increased. Consequently, the data show that the preconditioning period permits satisfactory operation of the process with high yields of desired products in the productive phase, with good resistance of catalyst to fragmentation and the production of a gasoline fraction of high anti-detonation quality. An inspection of the gasoline product during the periods below indicated is as follows:—

	Period	ASTM O.N.	ASTM + 2cc. TEL	Res. Clear	Res. + 2cc. TEL	RVP
	D	64.0	71.4	72.0	81.4	6.7
120	E	64.3	74.9	74.8	83.6	6.6
	F	60.6	72.4	72.0	82.8	6.4

By suitable treating, Res. clear O.N. can be raised to 90 or better.

Another feature of this invention is that during the several periods described, oxygenated hydrocarbons were formed. For example, during Period A, oxygenated compounds were found in both the oil and water layers. During Period A, 13 cc. oxygenated compounds (calculated as ethyl alcohol) per cubic meter of $H_2 + CO$ consumed were found in the water layer. In Period B, a similar amount of oxygenated compounds were found. In Period C, 27 cc. ethyl alcohol were found; in Period D, 28 cc. ethyl alcohol; in Period E, 23 cc.; and in Period F, 14 cc.

While improvements in connection with a synthetic ammonia catalyst have been described in detail, it will be understood that other forms of iron may be used, such as pyrites ash, red iron oxide or precipitated iron.

Also, these improvements include continuous adjustment of the H_2 to CO ratio during the synthesis process, that is to say, conducting the operation so that the H_2 to CO ratio may be changed without interrupting the process.

To recapitulate, this invention relates to operating a hydrocarbon synthesis process in fluidized operation using a powdered iron catalyst under conditions such that good yields are obtained by the severe conditions, that is high temperature ($600^\circ F.$ and above), high pressures (350 lbs./sq. inch and above) and relatively low ratios of hydrogen to carbon monoxide (below 2:1) and at the same time prevent serious physical disintegration of the powdered iron catalyst.

Having now particularly described and ascertained the nature of our said invention and in what manner the same is to be performed, we declare that what we claim is:—

1. A method of synthesizing hydro-

carbons and oxygenated hydrocarbons from a gas mixture containing hydrogen and carbon monoxide which comprises contacting the said gas mixture with a fluidized bed of powdered iron catalyst in a reaction zone at an elevated temperature and pressure comprising first subjecting the catalyst to a preconditioning treatment substantially at synthesis conditions of temperature and pressure with a gas mixture containing a molar ratio of hydrogen to carbon monoxide of at least 2.5 and preferably more than 3 molecules of hydrogen per molecule of carbon monoxide whereby the catalyst is converted into a form resistant to fragmentation and thereupon continuing the synthesis process with a gas mixture containing a lower ratio of hydrogen to carbon monoxide, preferably about 2 molecules of hydrogen per molecule of carbon monoxide.

2. A method as claimed in claim 1 wherein the molecular ratio of hydrogen to carbon monoxide in the preconditioning treatment is between 3.5 and 10 to 1.

3. A method as claimed in either of claims 1 or 2 wherein the preconditioning treatment is conducted for a period of from 10 to 300 hours, preferably from 40 to 200 hours.

4. A method as claimed in any of claims 1 to 3 wherein the preconditioning treatment is conducted under a total pressure of over 350 lbs./sq. inch, preferably about 400 lbs./sq. inch.

5. A method of synthesizing hydrocarbons and oxygenated hydrocarbons from gas mixtures containing hydrogen and carbon monoxide as hereinbefore described.

Dated this 26th day of July, 1948.

DAVID T. CROSS,

Brettenham House, Lancaster Place,
London, W.C.2,

Agent for the Applicants.

Leamington Spa: Printed for His Majesty's Stationery Office, by the Courier Press.—1951.

Published at The Patent Office, 25, Southampton Buildings, London, W.C.2, from which copies, price 2s. per copy; by post 2s. 1d. may be obtained.

This Drawing is a reproduction of the Original on a reduced scale

