

PATENT SPECIFICATION

730,487



Date of Application and filing Complete

Specification: Oct. 6, 1952.

No. 24991/52.

Application made in Germany on Oct. 9, 1951.

Complete Specification Published: May 25, 1955.

Index at acceptance:—Glasses 1(1), F3B1; and 2(3), B1G.

COMPLETE SPECIFICATION

Process for the Catalytic Hydrogenation of Carbon Monoxide

We, RUHRCHEMIE AKTIENGESSELLSCHAFT, of Oberhausen-Holten, Germany, a German Company, and LURGI GESELLSCHAFT FÜR WÄRMETECHNIK M.B.H., of Frankfurt am Main, Heddernheim, Germany, a German Company, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

The invention relates to a process for the hydrogenation of carbon monoxide in the presence of an iron catalyst.

15 It is known that, in the catalytic hydrogenation of carbon monoxide, primary products may be obtained which differ largely both in their chemical nature and in their boiling ranges. This variety of products 20 is obtained by varying the synthesis conditions, particularly with respect to the pressure, temperature, gas throughput and gas recycling, as well as by using catalysts of different composition and catalysts 25 which have been prepared by different methods. For iron catalysts, these conditions are very characteristic. In general, a catalyst of a given composition which has been prepared by a given method 30 results, in the main, in the formation of synthesis products of a certain composition. For the production of primary products having a high content of oxygen-containing organic compounds, strongly 35 alkaliised iron catalysts have proved to be useful. Only rarely has it been reported that different primary products are obtainable with the same catalyst, merely by selecting the conditions for the syn- 40 thesis operation, particularly in respect of the gas throughput.

It is known that the inner surface area of catalysts is of decisive importance for their efficiency, particularly with respect 45 to the chemical nature and the boiling

range of the primary products. (Reference is made to the work of Tramm "Zur Technik der Kohlenoxydhydrierung," published in "Erdoel und Kohle," Vol. 5, pp. 10-17, particularly Fig. 9 and the 50 left-hand column of page 14, and in "Brennstoff-Chemie," Vol. 33, pp. 21-30, particularly page 27, left-hand column, Fig. 9.)

It has now been found that by the use 55 of a catalyst of a given composition prepared by a given method and thus having a certain surface area, primary products having a high content of high boiling hydrocarbons may be obtained by the 60 hydrogenation of carbon monoxide.

According to the invention, a process for the catalytic hydrogenation of carbon monoxide comprises contacting a gas mixture containing hydrogen and carbon 65 monoxide in synthesis proportions with an iron-containing catalyst which is unsupported or which contains only a small quantity of supporting material, at a temperature in the range of 175°-300°C., 70 at an elevated pressure not exceeding 100 atmospheres gauge and at a rate of from 10 to 200 volumes of fresh synthesis gas per volume of catalyst per hour, the iron in the catalyst having been obtained by 75 precipitation from a solution of an iron salt at a pH value in the range 6.8-7.5, the catalyst having an SiO₂ content of from 5% to 15% obtained by direct impregnation with an alkali-metal silicate, 80 and having an alkali content (calculated as K₂O) of from 2% to 6%, the SiO₂ and the K₂O contents being by weight and relative to the total iron content of the catalyst, the catalyst having an inner surface area of from 180-230 square metres 85 per gram of the total iron in the catalyst and having been reduced prior to use to convert from 10% to 50% of the total iron into the elementary state. 90

Where the catalyst is supported, the small quantity of supporting material in the catalyst may, for example, constitute up to 10% by weight of the catalyst. Suitable substances for use as the supporting material are, for example, kieselguhr, alumina, bauxite and asbestos. The supporting material, when used, may be suspended in the solution of the iron salt or in the solution of the precipitant prior to the precipitation, or it may be added during the process of precipitation. It is preferred, however, to add the supporting material, when used, to the solution immediately the precipitation of the iron has been completed.

The alkali content of the catalyst is preferably in the range 3-4%, the inner surface area of the catalyst is preferably from 200 to 230 square metres per gram of total iron in the catalyst, and from 20% to 30% of the total iron in the catalyst is preferably in the elementary state.

The alkali content of the catalyst may be provided in part by the precipitant used for the precipitation of the iron catalyst, the washing of the precipitated catalyst mass being then limited to permit some of the alkali-metal compound or compounds to remain in the precipitate. Alternatively, the precipitate may be washed substantially free from alkali-metal compounds, the alkali content of the catalyst being then introduced by impregnating the precipitate with an alkali-metal silicate to obtain the desired content of SiO_2 . Any excess of alkali which is thereby introduced may be removed by means of dilute nitric acid. Thus the desired content of silicic acid (SiO_2) may be obtained by impregnating the precipitated mass with commercial alkali-metal silicate having a ratio of $\text{K}_2\text{O}:\text{SiO}_2$ of 1:2.5 by weight. It will be understood that when the alkali-metal in the catalyst or in the silicate is not potassium, the alkali metal is expressed as the equivalent of K_2O . The silicic acid (SiO_2) remains quantitatively in the precipitated catalyst mass and cannot be or is not removed therefrom by any chemical step employed in the course of the production of the catalyst.

The $\text{K}_2\text{O}:\text{SiO}_2$ ratio in the catalyst is advantageously adjusted to a value of from 1:1 to 1:5 by weight. Such a ratio will give particularly favourable results with respect to the life and the activity of the catalyst. To obtain a ratio of 1: more than 2.5, the catalyst mass impregnated with the alkali-metal silicate, for example, waterglass, is neutralised with dilute nitric acid while maintaining a pH value of 6.5-8, thereby dissolving out a more or less large proportion of the alkali-metal and shifting the ratio $\text{K}_2\text{O}:\text{SiO}_2$ in favour of

the silicic acid (SiO_2).

If a $\text{K}_2\text{O}:\text{SiO}_2$ ratio of 1: less than 2.5 is desired, an incomplete washing of the precipitated catalyst mass is advantageously effected, that is, the residual alkali content of the precipitate is adjusted to 1-2% (calculated as K_2O and based on the weight of the total iron in the precipitate). By the subsequent direct impregnation with the alkali-metal silicate, it is possible to obtain $\text{K}_2\text{O}:\text{SiO}_2$ ratios which are lower than 1:2.5, such, for example, as 1:1.5 or even 1:1.

The desired content of free iron in the catalyst is obtained by the use of suitable reduction conditions. The reduction is effected with gases containing hydrogen and/or carbon monoxide at temperatures within the range 175°C to 320°C , and preferably at temperatures between 200°C and 250°C . A high gas velocity of, for example, 1.2 metres per second and preferably 1.2-1.5 metres per second (calculated at room temperature and at normal atmospheric pressure) has been found to be advantageous.

The inner surface area of the catalyst is a function (a) of the alkali content, (b) of the SiO_2 content and (c) of the quantity of the total iron which is in the elementary state. The determination of the inner surface area of the catalyst is effected by the preparation of an adsorption isotherm and its evaluation by the method of Brunauer, Emmet and Teller (the so-called BET method). The apparatus required consists substantially of a graduated burette in which the volume of the gas to be adsorbed, such as nitrogen or argon, is measured, a manometer for the determination of the gas pressure, and a small flask in which the adsorbing substance to be tested is placed.

The catalyst may contain one or more promoters, such as copper, silver, lime or metals of 5th, 6th or 7th groups of the periodic system.

The invention is illustrated in the following example.

EXAMPLE

A boiling solution which contained 45 grams of iron, 0.45 grams of copper and 2.5 grams of CaO in solution in the form of their nitrates was added within 2 minutes to a boiling solution of sodium carbonate so that the pH value upon termination of the precipitation was 7.1. The mixture was then heated for a short time and immediately thereafter filtered in the hot state. The filtered mass was washed with hot distilled water so that the residual alkali content (calculated as K_2O) in the mass was 0.6% by weight based on the total iron content of the mass.

The moist catalyst mass was cooled and

impregnated with an aqueous solution of potassium silicate having a concentration of 20% and a $K_2O : SiO_2$ ratio of 1 : 2.5 by weight, the quantity of the potassium silicate solution used being such that the total alkali content of the impregnated catalyst mass was 3.6% (calculated as K_2O) by weight of the total iron in the mass. The content of silicic acid (SiO_2) in the impregnated mass was 7.8% by weight of the total iron.

The mass was dried at a temperature of $110^\circ C$., crushed and sieved to a grain size of between 2 mm and 4 mm.

The granulated catalyst mass was reduced for 60 minutes at a temperature of $250^\circ C$. with a gas mixture consisting of 75% of hydrogen and 25% of nitrogen using a superficial gas velocity of 1.4 metres per second (calculated at room temperature and at normal atmospheric pressure). 26% of the total iron in the reduced catalyst was then in the elementary state.

4.8 litres of the reduced catalyst mass were charged into a double-tube reaction vessel consisting of two concentric tubes, the catalyst being disposed in the annular space between the two tubes whilst a heat transfer medium was passed through the inner tube. Water gas was then contacted with the catalyst at a synthesis pressure of 30 atmospheres gauge and at a temperature of $212^\circ C$. and at the rate of 100 volumes of fresh gas per volume of catalyst per hour, with the use of a recycle ratio of 2.5 : 1 (2.5 volumes of recycle gas per volume of fresh gas). The $CO : H_2$ ratio in the water gas was 1 : 1.19.

The $CO + H_2$ conversion obtained under these conditions was 65%, the methane formation being 4.0%, and the usage or consumption ratio being 1 : 1.53. The proportion of products boiling above $320^\circ C$. constituted more than 75% of the liquid product.

A further catalyst was prepared in a manner similar to that described above, except that the washing of the precipitated mass was less intensive to leave a residual K_2O content of 1.5% instead of 0.6%. The same quantity of the same solution of potassium silicate as that described above, was used to impregnate the precipitated mass. When the reduced catalyst was used in synthesis under the conditions described above, the proportion of high boiling hydrocarbons in the product was somewhat higher.

What we claim is:—

1. A process for the catalytic hydrogenation of carbon monoxide, which comprises contacting a gas mixture containing hydrogen and carbon monoxide in synthesis proportions with an iron-contain-

ing catalyst which is unsupported or which contains only a small quantity of supporting material, at a temperature in the range 175° – $300^\circ C$., at an elevated pressure not exceeding 100 atmospheres gauge and at a rate of from 10 to 200 volumes of fresh synthesis gas per volume of catalyst per hour, the iron in the catalyst having been obtained by precipitation from a solution of an iron salt at a pH value in the range 6.8–7.5, the catalyst having an SiO_2 content of from 5% to 15% obtained by direct impregnation with an alkali-metal silicate, and having an alkali content (calculated as K_2O) of from 2% to 6%, the SiO_2 and the K_2O contents being by weight and relative to the total iron content of the catalyst, the catalyst having an inner surface area of from 180–230 square metres per gram of the total iron in the catalyst, and having been reduced prior to use to convert from 10% to 50% of the total iron into the elementary state.

2. A process according to Claim 1, in which precipitation of the solution of the iron salt is effected at a pH value not greater than 7.1.

3. A process according to Claim 1 or Claim 2, in which the alkali content is in the range 3%–4%.

4. A process according to any one of the preceding claims, in which from 20%–30% of the iron in the catalyst is in the elementary state.

5. A process according to any one of the preceding claims, in which the inner surface area of the catalyst is from 200–220 square metres per gram of the total iron in the catalyst.

6. A process according to any one of the preceding claims, in which the catalyst contains one or more promoters, such as lime, copper, silver and metals of the 5th to the 7th groups of the periodic system.

7. A process according to any one of the preceding claims, in which the precipitation of the iron from the solution is effected with an alkali-metal compound, the precipitated mass being then incompletely washed whereby, after impregnation of the mass with the alkali-metal silicate, a catalyst is obtained in which the numerical value of the ratio $SiO_2 : K_2O$ is less than 2.5.

8. A process according to any one of Claims 1 to 6, in which the precipitation of the iron from the solution is effected by an alkali-metal compound, the precipitated mass being thereafter washed for substantially complete removal of alkali-metal compounds, the washed mass being then impregnated with an alkali-metal silicate, the alkali-metal content in the catalyst being thereafter lowered by treatment of the mass with nitric acid whilst

- maintaining a pH value of from 6.5 to 8 to yield a catalyst in which the numerical value of the ratio $\text{SiO}_2:\text{K}_2\text{O}$ is greater than 2.5.
- 5 9. A process for the production of high boiling hydrocarbons by the hydrogenation of carbon monoxide, substantially as hereinbefore described.
10. A process for the catalytic hydrogenation of carbon monoxide, substantially 10 as described in the Example.
11. Hydrocarbons whenever obtained by the process of any preceding claim.
- EDWARD EVANS & CO.,
14-18, High Holborn, London, W.C.1.
Agents for the Applicants.

Printed for Her Majesty's Stationery Office by Wickes & Andrews, Ltd., E.C.4. 684/2.—1955.
Published at The Patent Office, 25, Southampton Buildings, London, W.C.2, from which copies may be obtained.