



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C10J 3/46		A1	(11) International Publication Number: WO 95/09901 (43) International Publication Date: 13 April 1995 (13.04.95)
(21) International Application Number: PCT/US94/11170 (22) International Filing Date: 30 September 1994 (30.09.94) (30) Priority Data: 08/130,921 4 October 1993 (04.10.93) US (60) Parent Application or Grant (63) Related by Continuation US 08/130,921 (CON) Filed on 4 October 1993 (04.10.93)		(74) Agents: RODMAN, Charles, B. et al.; Rodman & Rodman, 7-11 South Broadway, White Plains, NY 10601 (US). (81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report.</i> <i>With amended claims and statement.</i>	
(71) Applicant (for all designated States except US): TEXACO DE- VELOPMENT CORPORATION [US/US]; 2000 Wetchester Avenue, White Plains, NY 10650 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): KHAN, Motasimur, Rashid [US/US]; 19 Partners Road, Wappinger Falls, NY 12590 (US). ALBERT, Christine, Cornelia [US/US]; 579 Westbrook Drive, Peekskill, NY 10566 (US). DeCANIO, Stephen, Jude [US/US]; 2 Thittle Drive, Montgomery, NY 12549 (US).			
(54) Title: LIQUEFACTION AND PARTIAL OXIDATION OF PLASTIC MATERIALS			
(57) Abstract A process for upgrading plastic material containing inorganic filler or reinforcement material for use as feedstock in a partial oxidation gas generator for the production of raw synthesis gas, fuel gas, or reducing gas. The plastic material is granulated and partially liquefied by heating in a closed autoclave at a temperature in the range of about 400 °F to 495 °F and a pressure in the range of about 150 psig to 750 psig while the plastic material is in contact with a pumpable hydrocarbonaceous liquid solvent. A pumpable slurry is thereby produced comprising solubilized plastic, unsolubilized plastic, hydrocarbonaceous liquid solvent, separated inorganic material and unseparated inorganic material. After removing the separated inorganic material, the remainder of the slurry is then reacted by partial oxidation to produce said raw synthesis gas, fuel gas or reducing gas.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LIQUEFACTION AND
PARTIAL OXIDATION OF PLASTIC MATERIALS

FIELD OF THE INVENTION

This invention relates to an environmentally safe method for disposing of scrap plastic materials. More particularly, it pertains to a process for upgrading scrap plastic materials to produce a pumpable slurry of hydrocarbonaceous liquid solvent and partially liquefied scrap solid carbonaceous plastic-containing material and introducing said slurry into a partial oxidation gasifier for the production of synthesis gas, reducing gas, or fuel gas.

Scrap plastics are solid organic polymers and are available in such forms as sheets, extruded shapes, moldings, reinforced plastics, laminates, and foamed plastics. About 60 billion pounds of plastics are sold in the United States each year. For example, automobiles are increasingly being manufactured containing more plastic parts. A large part of these plastic materials wind up as scrap plastics in landfills. Although plastics account for only a small portion of the waste dumped in landfills i.e. about 7 wt. % and about 20 percent by volume, burying them is getting increasingly difficult. The cost of landfilling this material in 1993 is between \$12 to \$100 per ton (excluding shipping costs); and this cost is rising. Landfills are not universally viewed as an acceptable, or even a tolerable option for the disposal of plastic materials. Due to the combined effects of the unpopularity of existing facilities and the need for land to allow normal growth of populations, new landfills have been all but banned in many parts of the world. Existing facilities are also facing finite limits as to how long they may continue to function. Also, toxic wastes from buried plastics seep into and pollute underground streams which are commonly the source of our fresh water. Further, on-site burning

or incineration which are alternative disposal methods are in disfavor because they generate heavy air pollution from noxious gases and soot. With respect to recycling plastics, it has been economically feasible to recycle only about 1 wt. % of the scrap plastics. It is obvious from the aforesaid that the disposal of scrap plastics is one of the nation's most pressing environmental problems.

Advantageously by the subject environmentally acceptable process, a wide range of plastic feedstocks are partially liquefied for volume reduction and comparatively low cost disposal by partial oxidation. Useful synthesis gas, reducing gas or fuel gas is produced. Further, the relatively medium heating value of the plastic material e.g. greater than about 3,000 Btu/lb is made available for heating internal process streams or producing by-product hot water or steam.

SUMMARY OF THE INVENTION

This invention relates to an environmentally acceptable process for the partial oxidation of a pumpable slurry of hydrocarbonaceous liquid solvent and partially liquefied solid carbonaceous plastic material containing inorganic filler or reinforcement material; wherein synthesis gas, reducing gas, or fuel gas is produced by said process comprising the steps of:

- (1) granulating plastic material containing inorganic filler or reinforcement material;
- (2) partially liquefying the granulated plastic material from (1) by heating in a closed autoclave at a temperature in the range of about 400°F to 495°F and a pressure in the range of about 150 psig to 750 psig while said plastic material is in contact with a pumpable hydrocarbonaceous liquid solvent in the amount of about 1 to 5 parts by wt. of said hydrocarbonaceous liquid per part by weight of plastic material; wherein said heating is continued until a pumpable slurry mixture is

produced which when cooled to room temperature and pressure comprises the following ingredients in weight percent:

- a. solubilized plastic 20 to 30,
 - 5 b. unsolubilized plastic 5 to 15,
 - c. hydrocarbonaceous liquid solvent 45 to 55,
 - d. separated inorganic material 1 to 15,
 - e. unseparated inorganic material 5 to 15;
- (3) separating said separated inorganic material
- 10 (2)(d) from the remainder of said slurry mixture in (2); and
- (4) reacting by partial oxidation with a free-oxygen containing gas in the presence of a temperature moderator the remainder of said slurry
- 15 mixture from (3) to produce raw synthesis gas, fuel gas, or reducing gas.

DESCRIPTION OF THE INVENTION

Scrap plastics are disposed of by the process of the subject invention without polluting the nation's

20 environment. Simultaneously, useful by-product nonpolluting synthesis gas, reducing gas, fuel gas and nonhazardous slag are produced.

The scrap plastic materials which are processed as described herein into a pumpable slurry fuel feed for

25 a partial oxidation gas generator include at least one solid carbonaceous thermoplastic or thermosetting material that contains associated inorganic matter e.g. fillers and reinforcement material. Sulfur is also commonly found in scrap plastics. Scrap plastic

30 materials may be derived from obsolete equipment, household containers, packaging, industrial sources and junked automobiles. The mixture of plastics is of varying age and composition. With the presence of varying amounts of incombustible inorganic matter

35 compounded in the plastic as fillers, catalysts, pigments and reinforcing agents, recovery of the plastic material

is generally impractical. Further, complete combustion can release toxic-noxious components including volatile metals and hydrogen halides. Associated inorganic matter in the scrap solid carbonaceous plastic includes fillers such as titania, talc, clays, alumina, barium sulfate and carbonates. Catalysts and accelerators for thermosetting plastics include tin compounds for polyurethanes, and cobalt and manganese compounds for polyesters. Dyes and pigments such as compounds of cadmium, chromium, cobalt, and copper; non-ferrous metals such as aluminum and copper in plastic coated wire cuttings; metal films; woven and nonwoven fiber glass, graphite, and boron reinforcing agents; steel, brass, and nickel metal inserts; and lead compounds from plastic automotive batteries. Other heavy metals e.g. cadmium, arsenic, barium, chromium, selenium, and mercury may be also present. The inorganic constituents are present in the solid carbonaceous plastic-containing material in the amount of about a trace amount to about 60 wt. % of said solid carbonaceous plastic-containing material, such as about 1 to 20 wt. %. The scrap plastic material may be in the form of sheets, extruded shapes, moldings, reinforced plastics, and foamed plastics.

The slurring medium comprises a pumpable liquid hydrocarbonaceous solvent in the amount of about 30 to 90 wt. %. By definition, the term liquid hydrocarbonaceous solvent as used herein to describe suitable liquid solvents is a liquid hydrocarbonaceous fuel selected from the group consisting of liquefied petroleum gas, petroleum distillates and residues, gasoline, naphtha, kerosine, crude petroleum, asphalt, gas oil, residual oil, tar sand oil and shale oil, coal derived oil, aromatic hydrocarbons (such as benzene, toluene, xylene fractions), coal tar, cycle gas oil from fluid-catalytic-cracking operations, furfural extract of coker gas oil, and mixtures thereof. Waste hydrocarbon motor oil may also be used as a liquid solvent.

Hydrocarbon oils having the following properties are suitable: initial atmospheric boiling point, greater than 500°F; Neutralization No., mg KOH/g 0.70 to 1.0; and Aniline point °F 100 to 110. Other suitable oils comply with ASTM specification D2226, Types 101 and 102. The expression "A and/or B" is used herein in its usual manner and means A or B or A and B.

Figure 1 gives a breakdown of 1991 sales in the United States of solid carbonaceous plastics.

Figure 1

Million lbs.

	<u>Material</u>	<u>1991</u>
	Acrylobutadienestyrene (ABS)	1,125
	Acrylic	672
15	Alkyd	315
	Cellulosic	840
	Epoxy	428
	Nylon	536
	Phenolic	2,556
20	Polyacetal	140
	Polycarbonate	601
	Polyester, thermoplastic	2,549
	Polyester, unsaturated	1,081
	Polyethylene, high density	9,193
25	Polyethylene, low density	12,143
	Polyphenylene-based alloys	195
	Polypropylene and copolymers	8,155
	Polystyrene	4,877
	Other styrenes	1,180
30	Polyurethane	2,985
	Polyvinylchloride and copolymers	9,130
	Other vinyls	120
	Styrene acrylonitrile (SAN)	117
	Thermoplastic elastomers	584
35	Urea and melamine	1,467
	Others	345
	Total	60,598

The solid carbonaceous plastic-containing material that contains associated inorganic matter e. g. filler or reinforcement material, has a higher heating value (HHV) in the range of about 3000 to 19,000 BTU per lb of solid carbonaceous plastic-containing material.

The plastic-containing material is granulated by conventional means to a maximum particle dimension of about 1/4", such as about 1/8". Granulating is the preferred method for reducing the size of plastic. Any conventional plastic granulator and mill may be used. For example, a granulator will readily shred/grind solid plastic pieces to a particle size which passes through ASTM E 11 Alternative Sieve Designation 1/4" or less. A mill can take the product from the granulator (i.e., -1/4") and readily convert it to smaller sizes (-1/8" or less), such as ASTM E11 Alternative Sieve Designation No. 7. For example, a suitable granulator and mill are made by Enteleter Inc., 251 Welton St., Hamden, CT 06517. The ash content for an as-received granulated sample of automotive crusher plastic residue (ACR) is 58.2 wt %.

The granulated solid carbonaceous plastic-containing material is mixed together with a liquid slurring medium comprising a liquid hydrocarbonaceous solvent to produce a pumpable slurry having a solids content in the range of about 15 to 50 wt.% and having a minimum higher heating value (HHV) of about 4500 BTU/lb. of slurry.

The pumpable slurry is introduced into a closed autoclave where the granulated plastic material is directly contacted and heated by said pumpable hydrocarbonaceous liquid solvent which is present in the amount of about 1 to 5 parts by wt. of said hydrocarbonaceous liquid solvent per part by wt. of plastic material. The temperature in the autoclave is in the range of 400°F to 495°F. The pressure in the autoclave is in the range of 150 psig to 750 psig. Under these conditions condensate formation due to cracking and residue formation due to coking are avoided. Liquefaction of a portion of the plastic by contact with the hot hydrocarbonaceous liquid solvent takes place over a period of time in the range of about 20 min. to 6.0 hrs, such as about 30 minutes. The partial liquefaction

of the granulated plastic is continued until a pumpable slurry is produced which when cooled to room temperature and pressure comprises the following ingredients in wt. %:

- | | | |
|----|----------------------------------|----------|
| a. | solubilized plastic | 20 to 30 |
| b. | unsolubilized plastic | 5 to 15 |
| c. | hydrocarbonaceous liquid solvent | 45 to 55 |
| d. | separated inorganic material | 1 to 15 |
| e. | unseparated inorganic material | 5 to 15 |

The solubilized plastic is that portion of the granulated plastic material that is liquefied by contact with hydrocarbonaceous liquid solvents. The unsolubilized plastic is that portion of the granulated plastic that remains undissolved after said solvent treatment. The separated inorganic material is that portion of the inorganic material produced by the solvent liquefaction treatment of the granulated plastic material that may be easily separated from the remainder of the slurry by settling, screening, filtering, or centrifuging. The density of the separated inorganic material is greater than 1.2. Typical separated inorganic compounds are selected from the group consisting of silica, alumina, calcium carbonate, and mixtures thereof. Also included are the oxides and/or sulfides of Na, Ca, Mg, Fe, and mixtures thereof. In one embodiment, at least a portion of the separated inorganic material is recycled to the autoclave for additional heating in said hydrocarbonaceous liquid solvent.

Unseparated inorganic material is that portion of the inorganic material produced by the solvent liquefaction treatment of the granulated plastic material that remains combined in the slurry and cannot be easily separated from the slurry by settling, screening, filtering, or centrifuging. Typical unseparated inorganic material includes mixtures of the oxides and/or sulfides of the following elements: Al, Ba, Ca, Cu, Fe, K, Mg, Mn, Ni, P, Pb, Si, Sr and Ti. The particle size of

the unseparated inorganic material is less than 0.2 mm., which is less than the particle size of the separated inorganic material.

5 The pumpable slurry of granulated solid carbonaceous plastic-containing material and liquid slurring medium, a temperature moderator e.g. H₂O, CO₂, and a stream of free-oxygen containing gas are introduced into the reaction zone of a free-flow unobstructed downflowing vertical refractory lined steel wall pressure
10 vessel where the partial oxidation reaction takes place for the production of synthesis gas, reducing gas, or fuel gas. A typical gas generator is shown and described in coassigned U.S. Pat. No. 3,544,291, which is incorporated herein by reference.

15 A two, three or four stream annular type burner, such as shown and described in coassigned U.S. Pat. Nos. 3,847,564, and 4,525,175, which are incorporated herein by reference, may be used to introduce the feedstreams into the partial oxidation gas
20 generator. With respect to U.S. Pat. No. 3,847,564, free-oxygen containing gas, for example in admixture with steam, may be simultaneously passed through the central conduit 18 and outer annular passage 14 of said burner. The free-oxygen containing gas is selected from the group
25 consisting of substantially pure oxygen i.e. greater than 95 mole % O₂, oxygen-riched air i.e. greater than 21 mole % O₂, and air. The free-oxygen containing gas is supplied at a temperature in the range of about 100°F. to 1000°F. The pumpable slurry of granulated solid
30 carbonaceous plastic-containing material and hydrocarbonaceous liquid solvent is passed into the reaction zone of the partial oxidation gas generator by way of the intermediate annular passage 16 at a temperature in the range of about ambient to 650°F.

35 The burner assembly is inserted downward through a top inlet port of the noncatalytic synthesis gas generator. The burner extends along the central

longitudinal axis of the gas generator with the downstream end discharging a multiphase mixture of fuel, free-oxygen containing gas, and temperature moderator such as water, steam, or CO₂ directly into the reaction zone.

The relative proportions of fuels, free-oxygen containing gas and temperature moderator in the feedstreams to the gas generator are carefully regulated to convert a substantial portion of the carbon in the slurry, e.g., up to about 90% or more by weight, to carbon oxides; and to maintain an autogenous reaction zone temperature in the range of about 1800°F. to 3500°F. Preferably the temperature in the gasifier is in the range of about 2400°F. to 2800°F., so that molten slag is produced. The pressure in the partial oxidation reaction zone is in the range of about 1 to 30 atmospheres. Further, the weight ratio of H₂O to carbon in the feed is in the range of about 0.2 - 3.0 to 1.0, such as about 0.5 - 2.0 to 1.0. The atomic ratio of free-oxygen to carbon in the feed is in the range of about 0.8 - 1.5 to 1.0, such as about 0.9 - 1.2 to 1.0. By the aforesaid operating conditions, a reducing atmosphere comprising H₂ + CO is produced in the reaction zone along with nontoxic slag.

The dwell time in the partial oxidation reaction zone is in the range of about 1 to 15 seconds, and preferably in the range of about 2 to 8 seconds. With substantially pure oxygen feed to the gas generator, the composition of the effluent gas from the gas generator in mole % dry basis may be as follows: H₂ 10 to 60, CO 20 to 60, CO₂ 5 to 60, CH₄ nil to 5, H₂S+COS nil to 5, N₂ nil to 5, and Ar nil to 1.5. With air feed to the gas generator, the composition of the generator effluent gas in mole % dry basis may be about as follows: H₂ 2 to 20, CO 5 to 35, CO₂ 5 to 25, CH₄ nil to 2, H₂S+COS nil to 3, N₂ 45 to 80, and Ar 0.5 to 1.5. Unconverted carbon, ash, or molten slag are contained in the effluent gas

stream. Depending on the composition and use, the effluent gas stream is called synthesis gas, reducing gas, or fuel gas. For example, synthesis gas comprises mixtures of $H_2 + CO$ that can be used for chemical synthesis; reducing gas is rich in $H_2 + CO$ and is used in reducing reactions; and fuel gas comprises mixtures of $H_2 + CO$, and may also includes CH_4 . Advantageously, in the extremely hot reducing atmosphere of the gasifier, the toxic elements in the inorganic matter in the solid carbonaceous plastic-containing material are captured by the noncombustible constituents present and converted into nontoxic nonleachable slag. This permits the nontoxic slag to be sold as a useful by-product. For example, the cooled slag may be ground or crushed to a small particle size e.g. less than 1/8" and used in road beds or building blocks.

The hot gaseous effluent stream from the reaction zone of the synthesis gas generator is quickly cooled below the reaction temperature to a temperature in the range of about 250°F. to 700°F. by direct quenching in water, or by indirect heat exchange for example with water to produce steam in a gas cooler. The cooled gas stream may be cleaned and purified by conventional methods. For example, reference is made to coassigned U.S. Pat. No. 4,052,176, which is included herein by reference for removal of H_2S , COS , and CO_2 . Advantageously, when gasifying plastics that contain halides such as polyvinylchloride, polytetrafluoroethylene, by partial oxidation, the halide is released as hydrogen halide (i.e. HCl , HF) and is scrubbed out of the synthesis gas with water containing ammonia or other basic materials. Plastics that contain bromine-containing fire retardants may be similarly treated. Reference is made to coassigned U.S. 4,468,376 which is incorporated herein by reference.

The following examples illustrate the subject invention and should not be construed as limiting the scope of the invention.

EXAMPLES

Example 1

4 tons per day of a mixture comprising several types of plastic that are found in automobiles including unfilled, filled, and reinforced plastics from the following resins: polystyrene, polyamide, polyurethane, polyvinylchloride, polypropylene, and others are shredded to a particle dimension of less than about 1/8" and mixed with 4 tons per day of waste hydrocarbon motor oil having an initial atmospheric boiling point in the range of about 250 °F to 500°F. The ultimate chemical analysis of a typical shredded mixture of plastics is shown in Table I. The chemical analysis of the ash in the mixture of plastics is shown in Table II.

TABLE I

Dry Analysis
of Mixture of Plastics
In Example 1.

Weight
Percent

C	23.8
H	4.2
N	0.9
S	0.5
O	12.3
Ash	58.3

TABLE II

Chemical Analysis of the Ash Present
In the Mixture of Plastics
In Example 1.

5		<u>Wt. %</u>
	SiO ₂	33.20
	Al ₂ O ₃	6.31
	Fe ₂ O ₃	22.00
	CaO	29.20
10	MgO	0.94
	Na ₂ O	1.27
	K ₂ O	0.43
	TiO ₂	0.89
	P ₂ O ₃	0.92
15	Cr ₂ O ₃	0.28
	ZnO	2.31
	PbO	0.09
	BaO	0.80
	CuO	0.89
20	NiO	0.47

The aforesaid pumpable aqueous slurry of plastics and waste oil is partially liquefied in a closed autoclave at a temperature of 475°F and a pressure of 500 psig for 30 minutes. The pumpable slurry from the autoclave is filtered to remove separable inorganic material and the remaining portion is reacted with about 7 tons per day of oxygen gas by partial oxidation in a conventional free flow noncatalytic gas generator at a temperature of about 2400°F and a pressure of about 500 psig. Synthesis gas comprising H₂ + CO is produced along with about 3 tons of slag. Upon cooling, the slag is a coarse, glassy nonleachable material. If however, the same mixture of plastics were fully combusted in air, the slag may contain toxic elements, e.g. chromium in a leachable form.

Other modifications and variations of the invention as hereinbefore set forth may be made without departing from the spirit and scope thereof, and therefore, only such limitations should be imposed on the invention as are indicated in the appended claims.

5

WE CLAIM:

1. A partial oxidation process comprising:

(1) granulating plastic material containing inorganic filler or reinforcement material;

(2) partially liquefying the granulated plastic material from (1) by heating in a closed autoclave at a temperature in the range of about 400½F to 495½F and a pressure in the range of about 150 psig to 750 psig while said plastic material is in contact with a pumpable hydrocarbonaceous liquid solvent in the amount of about 1 to 5 parts by wt. of said hydrocarbonaceous liquid per part by weight of plastic material; wherein said heating is continued until a pumpable slurry is produced which when cooled to room temperature and pressure comprises the following ingredients in weight percent:

- | | |
|-------------------------------------|-----------|
| a. solubilized plastic | 20 to 30, |
| b. unsolubilized plastic | 5 to 15, |
| c. hydrocarbonaceous liquid solvent | 45 to 55, |
| d. separated inorganic material | 1 to 15, |
| e. unseparated inorganic material | 5 to 15; |

(3) separating said separated inorganic material (2)(d) from the remainder of said slurry in (2); and

(4) reacting by partial oxidation with a free-oxygen containing gas in the presence of a temperature moderator the remainder of said slurry from (3) to produce raw synthesis gas, fuel gas, or reducing gas.

2. The process of Claim 1 wherein the granulated solid carbonaceous plastic material from (1) is mixed with the liquid hydrocarbonaceous solvent from (2) to produce the pumpable slurry which is introduced into the autoclave in (2).

3. The process of Claim 1 wherein said pumpable hydrocarbonaceous liquid solvent is selected from the group consisting of liquefied petroleum gas, petroleum distillates and residues, gasoline, naphtha, kerosine, crude petroleum, asphalt, gas oil, residual oil, tar sand oil and shale oil, coal derived oil, aromatic hydrocarbons (such as benzene, toluene, xylene fractions), coal tar, cycle gas oil from fluid-catalytic-cracking operations, furfural extract of coker gas oil and mixtures thereof.

4. The process of Claim 1 wherein said pumpable hydrocarbonaceous liquid solvent meets ASTM Specification D2226, Types 101 and 102.

5. The process of Claim 1 wherein said hydrocarbonaceous liquid solvent is a hydrocarbon oil having the following properties: initial atmospheric boiling point greater than 500°F, Neutralization No., mg KOH/g 0.70 to 1.0, and aniline point °F 100 to 110.

6. The process of Claim 1 wherein said plastic material is selected from the group consisting of polyesters, polyurethane, polyamide, polystyrene, cellulose acetate, polypropylene, and mixtures thereof.

7. The process of Claim 1 where in (1) said plastic material is granulated to a particle size which passes through ASTM E11 Alternative Sieve Designation No. 7 or less.

8. The process of Claim 1 where in (2) said heating takes place for a period in the range of about 20 minutes to 6.0 hr.

9. The process of Claim 1 wherein the separated inorganic material (2)(d) has a density of 1.2.

10. The process of Claim 1 where in (3) said separated inorganic (2)(d) material is separated from the remainder of said slurry mixture by settling, screening, or centrifuging.

11. The process of Claim 1 wherein the separated inorganic material (2)(d) is selected from the group consisting of silica, alumina, calcium carbonate, the oxides and/or sulfides of iron, magnesium, calcium, and sodium, and mixtures thereof.

12. The process of Claim 1 provided with the step of recycling at least a portion of the separated inorganic material (2)(d) to the autoclave in (2) for additional heating in said hydrocarbonaceous liquid solvent.

13. The process of Claim 1 where in (4) said remainder of said slurry from (3) is reacted with a free oxygen containing gas by partial oxidation in a free-flow refractory lined vertical gas generator at a temperature in the range of about 1800°F to 3500°F, a pressure in the range of about 1 to 300 atmospheres, an atomic ratio O/C in the range of about 0.8 - 1.5 to 1.0, and a weight ratio of H₂O to carbon in the range of about 0.2 - 3.0 to 1.0, to produce a hot raw effluent gas stream comprising H₂, CO, CO₂, H₂O, H₂S, COS, and optionally N₂.

AMENDED CLAIMS

[received by the International Bureau on 15 March 1995 (15.03.95);
original claims 1 and 3 amended; remaining
claims unchanged (2 pages)]

1. A partial oxidation process comprising:

(1) granulating solid plastic material in the form of
sheets, extruded shapes, moldings, reinforced plastics,
laminates and foamed plastics, containing inorganic
filler or reinforcement material;

(2) partially liquefying the granulated plastic material
from (1) by heating in a closed autoclave at a
temperature in the range of about 400°F to 495°F and a
pressure in the range of about 150 psig to 750 psig while
said plastic material is in contact with a pumpable
hydrocarbonaceous liquid solvent in the amount of about
1 to 5 parts by wt. of said hydrocarbonaceous liquid per
part by weight of plastic material; wherein said heating
is continued until a pumpable slurry is produced which
when cooled to room temperature and pressure comprises
the following ingredients in weight percent:

- | | | |
|----|----------------------------------|-----------|
| a. | solubilized plastic | 20 to 30, |
| b. | unsolubilized plastic | 5 to 15, |
| c. | hydrocarbonaceous liquid solvent | 45 to 55, |
| d. | separated inorganic material | 1 to 15, |
| e. | unseparated inorganic material | 5 to 15; |

(3) separating said separated inorganic material (2) (d)
from the remainder of said slurry in (2); and

(4) reacting by partial oxidation with a free-oxygen
containing gas in the presence of a temperature moderator
the remainder of said slurry from (3) to produce raw
synthesis gas, fuel gas, or reducing gas, and a non-toxic
slag.

2. The process of Claim 1 wherein the
granulated solid carbonaceous plastic material from (1)
is mixed with the liquid hydrocarbonaceous solvent from
(2) to produce the pumpable slurry which is introduced
into the autoclave in (2).

3. The process of Claim 1 wherein said pumpable hydrocarbonaceous liquid solvent is selected from the group consisting of petroleum distillates and residues, crude petroleum, asphalt, gas oil, residual oil, tar sand oil and shale oil, coal derived oil, aromatic hydrocarbons, coal tar, cycle gas oil from fluid-catalytic-cracking operations, furfural extract of coker gas oil and mixtures thereof.

4. The process of Claim 1 wherein said pumpable hydrocarbonaceous liquid solvent meets ASTM Specification D2226, Types 101 and 102.

5. The process of Claim 1 wherein said hydrocarbonaceous liquid solvent is a hydrocarbon oil having the following properties: initial atmospheric boiling point greater than 500°F, Neutralization No., mg KOH/g 0.70 to 1.0, and aniline point °F 100 to 110.

6. The process of Claim 1 wherein said plastic material is selected from the group consisting of polyesters, polyurethane, polyamide, polystyrene, cellulose acetate, polypropylene, and mixtures thereof.

7. The process of Claim 1 where in (1) said plastic material is granulated to a particle size which passes through ASTM E11 Alternative Sieve Designation No. 7 or less.

8. The process of Claim 1 where in (2) said heating takes place for a period in the range of about 20 minutes to 6.0 hr.

9. The process of Claim 1 wherein the separated inorganic material (2) (d) has a density of 1.2.

STATEMENT UNDER ARTICLE 19

This statement accompanies the Amendment under Article 19.

Claims 1 and 3 have been amended to more precisely define the invention.

All of the amendments are identical to those made to the claims in the priority U.S. patent application Serial No. 08/130,921, upon which this PCT application is based. No new matter has been added.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/11170

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :C10J3/46

US CL :48/197R, 206, 209; 252/373

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 48/197R, 206, 209, DIGEST 7; 252/373; 585/240, 241

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,468,376 (SUGGITT) 28 August 1984, see entire document.	1-13
Y	US, A, 4,443,230 (STELLACCIO) 17 April 1984, see entire document.	1-13
Y	US, A, 4,108,730 (CHEN ET AL.) 22 August 1978, see entire document.	1-13
Y	FR, A, 2,357,637 (CHAPELET ET AL.) 10 March 1978, see entire document.	1-13
Y	DE, A, 2,922,553 (POBIEGLY ET AL.) 13 December 1979, see entire document.	1-13
Y	DE, A, 3,313,470 (MORSTADT) 18 October 1984, see entire document.	1-13

☒ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search	Date of mailing of the international search report
13 JANUARY 1995	FEB 1 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

PETER F. KRATZ

Telephone No. (703) 308-0196

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/11170

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y,E	US, A, 5,364,996 (CASTAGNOLI ET AL.) 15 November 1994, see entire document.	1-13