



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01B 3/20, 3/22, 3/28	A1	(11) International Publication Number: WO 97/04465 (43) International Publication Date: 6 February 1997 (06.02.97)
(21) International Application Number: PCT/NO96/00172 (22) International Filing Date: 10 July 1996 (10.07.96) (30) Priority Data: 952808 14 July 1995 (14.07.95) NO (71) Applicant (for all designated States except US): NORSK HYDRO A.S [NO/NO]; N-0240 Oslo (NO). (72) Inventors; and (75) Inventors/Applicants (for US only): PETTERSEN, Jarl, Markus [NO/NO]; Sleipneveien 73, N-3274 Larvik (NO). TANDE, Terje [NO/NO]; Hydralveien 10, N-3970 Langesund (NO). TANDE, Morten [NO/NO]; Skoglia 8b, N-3970 Langesund (NO). PALMGREN, Odd [NO/NO]; Lyngveien 28, N-3930 Porsgrunn (NO). (74) Agent: LILLEGRAVEN, Rita; Norsk Hydro a.s, N-0240 Oslo (NO).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ELECTRICAL INSULATING OIL BASED COMPOUND AND ITS USE (57) Abstract <p>The present invention relates to electrical insulating oil based compounds comprising mineral oils and oil soluble synthetic block-copolymers of polystyrene and synthetic rubber having molecular weights from 50.000-1.000.000. The oil component has preferably a content of aromates of 5-30 weight %. The compounds have high viscosity at low temperatures and are thin liquids at 40-80 °C. The gas absorption capacity of the compounds is high and they are especially useful as insulating compounds in paper wrapped cables, like high voltage DC (HVDC) power cables.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LT	Lithuania	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LR	Liberia	SZ	Swaziland
CS	Czechoslovakia	LT	Lithuania	TD	Chad
CZ	Czech Republic	LU	Luxembourg	TG	Togo
DE	Germany	LV	Latvia	TJ	Tajikistan
DK	Denmark	MC	Monaco	TT	Trinidad and Tobago
EE	Estonia	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	UG	Uganda
FI	Finland	ML	Mali	US	United States of America
FR	France	MN	Mongolia	UZ	Uzbekistan
GA	Gabon	MR	Mauritania	VN	Viet Nam

"ELECTRICAL INSULATING OIL BASED COMPOUND AND ITS USE"

The present invention relates to electrical insulating oil based compounds comprising mineral oils and oil soluble polymers. The compounds are especially useful as electrical insulator in paper wrapped cables, like high voltage DC (HVDC) power cables.

In transformers, starter motors, and other electrical equipment that generate considerable amount of heat, liquids are employed both as insulators and coolants. In cables, capacitors, and connections, insulation liquids are used as a functional component of the dielectric. Organic fluids with low viscosities, in particular mineral oils, are suited for insulating media or dielectrics, for instance, as filling for high-tension transformers, circuit breakers, cables or capacitors. Most liquid insulators consist of mineral oils or synthetic fluids.

Mineral oils, as defined in this application, are complex hydrocarbon mixtures obtained from petroleum oil by fractional distillation and refining. They combine important properties including high breakdown strength, good impregnation characteristics, and the ability to conduct large amounts of heat via convection. Mineral oils can also bind any gas produced during electrical discharge resulting in pronounced evaporation and decomposition. Depending on the predominant hydrocarbon, the oils can be classified as naphthenic or paraffinic based oils, however there is no sharp transition between these groups.

With respect to quantity, the transformer oils represent the major part of the insulating oils. The essential functions of the oil are, beside insulation of the power conductors, to remove the heat generated in the transformer by forced circulation with pumps or by

thermosiphon cooling. In order to achieve a satisfactory heat removal, low-viscosity mineral oils are used world-wide with excellent low-temperature properties.

Switch gear oils are used to protect the contacts of high-voltage circuit breakers against burning due to formation of arcs when the breaker is operated and also to achieve a faster power cut-off. Such oils must possess excellent insulating properties as well as a low viscosity even at low temperatures, in order to allow quick movement of the contact breaker and to fill the gap between the separating contacts.

Underground cables for the transport of medium and high-voltages power contain oil as the insulating medium. Insulation and heating problems can arise, depending on the voltage and power, such that oils with different viscosity grades are needed in cable technology: the higher transmitted voltage, the lower is the required viscosity of the cable oils in order to control heating of the cables, which is the result of ohmic losses in the conductor and of dielectric losses in the insulating material. The oil for the insulation of the voltage-carrying conductor is used to impregnate the multi-layer paper roll which surrounds the conductor. In the cases of high-voltage cables the conductor can be hollow and filled with oil. The oil in the paper roll is in contact with the oil in the hollow conductor via passages, so that the oil can expand into expansion chambers, placed at certain intervals, when the cable becomes hot. If the cable is cooled down, formations of cavities can occur. The formation of cavities in the paper insulation reduces the insulating effect, this in turn leads to gas evolution from the oil due to corona discharge. Both phenomena can create an electrical breakdown hazard.

Such cables, used for the transmission of AC voltages of up to 24 kV, are lapped with paper tapes which are impregnated with a more viscous insulating compound. There is no additional oil feeding system, thus all requirements with respect to insulation stability, particularly the prevention of cavitation, must be satisfied by the impregnating compound. Highly viscous impregnating substances are required in order to prevent migration of the compound from the wrapping resulting in local weakening of the insulation. The compound comprises a highly viscous mineral oil which is further thickened by the addition of natural resins or oil-soluble polymers.

Insulating compounds used in high voltage cables today, contain blends of mineral oils and synthetic homopolymers or refined rosin. The viscosity is high at low temperatures and low at high temperatures, however, the compound becomes a thin liquid first at 100-120°C . When the paper wrapped cables are impregnated, the insulating compound must be a thin liquid.

Accordingly the insulating compound used today must therefore be heated to above 100°C before impregnation, and then cooled down. This cooling step will prolong the production time.

The viscosity profile of the compounds used today does not properly secure that the insulating compound does not leak out of the cable at sub-sea temperatures (below 10°C).

Sparks caused by electrical discharges in gas or vacuum bubbles (cavities) in the insulating material in high voltage cables is a serious problem. The compounds used as insulating material in power cables today does not absorb hydrogen gas to a sufficient degree.

The main object of the present invention was to provide an electrical insulating compound having improved properties and not having the limitations and shortcomings of known electrical insulating compounds.

Another object was to provide a HVDC power cable electrical insulating compound with high viscosity at operating temperatures and a viscosity being suitable for impregnation at temperatures below 100°C. A compound having such a viscosity profile should secure that the impregnation of the paper wrapped cable can be performed at lower temperatures and at a higher rate than presently possible.

A further object of the invention was to provide a compound, which could reduce the risk of the formation of hydrogen gas bubbles or vacuum bubbles, and thereby lower the risk of electrical discharges in the cables.

The inventors carried out a comprehensive study of requirements to be met by the new compound. These studies concluded with the following characteristic properties which the new compound should possess :

- a) It should have the ability to absorb hydrogen gas under electrical stress and ionization.
- b) It should fulfil the ageing requirements. The dielectric dissipation factor ($\text{tg}\delta$ at 100°C) should not exceed 0.005 for oil having been exposed to air for 7 days at 125°C .
- c) It should have high viscosity at operating temperatures, but should have a steep decrease in viscosity with increasing temperature in order to enable impregnation at temperatures below 100°C . Thus it should be a thin liquid when the paper wrapped cables are impregnated. The insulating compound must penetrate the paper and fill the whole cable, accordingly the viscosity should be low at impregnating temperatures. It is also important that the insulating compound does not leak out during physical damage of the cable. Therefore the viscosity should be high at low temperatures.
- d) There should be substantially no asphaltenes in the compound.
- e) The total content of sulphur should be below 700 ppm.
- f) The compound should not contain sulphur in amounts resulting in corrosion.

Some important properties of the new compound are listed in more detail in table 1.

Table 1

Viscosity	< 300 mPas at $t > 80^{\circ}\text{C}$ >3.000 mPas at $t < 20^{\circ}\text{C}$
Dissipation factor ($\text{tg}\delta$) at 100°C	Newly made compound: < 0.002 After ageing: < 0.005
Dielectric strength (kV/2.5mm)	minimum 30
Gas absorption (mm^3/min)	> -2
Coefficient of expansion/ $^{\circ}\text{C}$	< 9×10^{-4}

When the inventors were looking for a compound which would fulfil all the above mentioned requirements, they found that by blending together mineral oils and synthetic block-copolymers, particularly polystyrene rubber, they would end up with useful compounds. These results lead to a comprehensive study of such mixtures. The conclusion drawn from these studies was that the following components would be applicable within the following definition :

Oil : Mineral oils. The oil should be predominantly naphthenic with relatively high content of aromates.

Polymer : Oil soluble, synthetic hydrocarbonic block-copolymer of polystyrene and synthetic rubber, having molecular weight from 50.000- 1.000.000. The rubber part should be ethylene-/buthylene-, isoprene- or butadiene rubber.

Sometimes it can be useful to add a compound which increase the gas absorption, i.e. alkylbenzene, like dodecylbenzene, dialkylbenzenes or diarylalkanes, to the mixture of oils and block-copolymers. Further, polyisobutylene can be added to increase the viscosity of the compound.

The ratio between the oils and the polymer was found to be of importance. Further it was found that it would be advantageous to apply different types of oils, for instance :

Oil 1 : Mineral oil with 10-30 weight% aromatic hydrocarbons.
Viscosity : 5 - 10 mPas/^oC at 25^oC
Boiling point : > 300^oC

Oil 2 : Hydrogenated, naphtenic mineral oil.
Viscosity: 5 - 10 mPas/^oC at 25^oC.
Boiling point : > 250^oC

Oil 3 : Hydrogenated, naphtenic mineral oil.
Viscosity : 90 - 100 mPas/^oC at 25^oC.
Boiling point : > 300^oC

The content of aromates in the oil component of the compound should preferably be 5-30 weight%.

The performed study revealed that the composition of the electrical insulating compound according to the invention should be within the following ranges :

Polymer : 3 - 10 % (weight/total weight)

Oil 1 : 10 - 90 % (weight/total weight)

Oil 2 : 0 - 15 % (weight/total weight)

Oil 3 : 0 - 85 % (weight/total weight)

The most suitable compositions for HVDC power cables were found to have the following compositions:

7

3 - 10 % (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block and the oil component comprises:

60 - 80 % (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons, 7 - 15 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point $>250^{\circ}\text{C}$ and 7 - 15 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point $>300^{\circ}\text{C}$.

or

3-10 % (weight/total weight) of a styrene-isoprene-styrene tri-block
60-70 % (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons and 20-30% (weight/total weight) of dodecylbenzene.

or

5.0-6.0 % (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block
45-75 % (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons and 20-50 % (weight/total weight) of a hydrogenated, naphtenic mineral oil.

or

3.0-10 % (weight/totaal weight) synthetic hydrocarbon block-copolymer,
10-15 % (weight/total weight) of an mineral oil with 10-30% aromatic hydrocarbons and 75-85 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point $>300^{\circ}\text{C}$.

Further it is preferred that the block-copolymer is a styrene-ethylene/buthylene-styrene tri-block or styrene-isoprene-styrene tri-block.

When the properties of the insulating oils were measured, the following methods were used :

Viscosity : Instrument : Bohlin VOR Rheometer
Conditions : Measuring system, C 25
Temperature : 80 - 4°C, 0.2-0.5°C/min.
Shear Rate : 0.581 s⁻¹

Gas absorption: Gassing of insulating liquids under electric stress and ionisation (IEC Standard Publication 628)

Dielectric dissipation factor (tg δ) or dielectric loss : Method : IEC 247.

Expansion coefficient (α) : Thermal volumetric expansion coefficient pro degree Kelvin (K⁻¹).

$$V = V_o (1 + \alpha t).$$

The scope and special features of the invention are as defined in the attached claims.

The invention will now be further explained in connection with the description of the figures and the examples.

Figs. 1 - 5 shows the viscosity profiles, viscosity as function of temperature, of the insulating compounds prepared in examples 1 - 4 compared with a known insulating compound. Curve I on the figures refers to the known compound and curve II to the exemplified compounds according to the invention.

Example 1

This example shows preparation of an electrical insulating oil based compound according to the invention. In figure 1, curve II is the viscosity profile of the compound shown. The known compound (Curve I) which the new compounds are compared with, is a commercially available insulating compound based on viscous mineral oil thickened by addition of oil-soluble polymers.

Recipe: 6.00 % (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block
70.50 % (weight/total weight) of oil 1
11.75 % (weight/total weight) of oil 2
11.75 % (weight/total weight) of oil 3

The oil components and the block copolymer are mixed in a reactor until the particles are evenly distributed. Then the reactor is heated to 80-120°C and when all the copolymer are dissolved the mixture is evacuated and the temperature is reduced to about 70°C. The mixture is subsequently filtered, preferably with diatomaceous earth.

The filtered compound had the following properties:

Dissipating factor (tgδ) at 100°C	:	New compound :	0.0020
		After ageing :	0.0027
Dielectric strength (kV/2.5 mm)	:	>60	
Gas absorption (mm ³ /min)	:	-10.8	
Specific gravity at 20°C (g/ml)	:	0.85	
Coefficient of expansion K ⁻¹	:	0.000676	

Example 2

This example shows preparation of an electrical insulating oil based compound containing an alkyl benzene, which secure high gas absorption. In figure 2, curve II, shows the viscosity profile of the compound.

Recipe : 10 % (weight/total weight) of a styrene-isoprene-styrene tri-block
65 % (weight/total weight) of oil 1
25 % (weight/total weight) of dodecylbenzene

The electrical insulating compound was prepared in the same way as the compound in example 1.

The compound has the following properties :

Dissipating factor ($\text{tg}\delta$) at 100°C	:	New compound	0.041
		After ageing	0.045
Dielectric strength (kV/2.5 mm)	:	36-46	
Gas absorption (mm^3/min)	:	-15	
Coefficient of expansion K^{-1}	:	0.00068	
Specific gravity at 20°C (g/ml)	:	0.85	

Example 3

This example shows the composition of some further electrical insulating compounds according to the invention. Their gas absorption properties are stated and their viscosity profile are shown in figure 3, curve II for recipe A and figure 4, curve II for recipe B.

Recipes :

- A) 5.0% (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block
 47.5% (weight/total weight) of oil 1
 47.5% (weight/total weight) of oil 2
- B) 6.0% (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block
 70.5% (weight/total weight) of oil 1
 23.5% (weight/total weight) of oil 2

The compounds had the following properties :

		A	B
Dissipating factor ($\text{tg}\delta$) at 100°C:	New compound	0.0020	0.0020
	After ageing	0.0030	0.0030
Dielectric strength (kV/2.5 mm) :		>40	>40
Gas absorption (mm^3/min) :		-2.0	-8.0
Coefficient of expansion K^{-1} :		0.0007	0.007
Specific gravity at 20°C (g/ml) :		0.85	0.85

Example 4

This example shows preparation of an insulating oil based compound having a high content of hydrogenated naphthenic mineral oil and a viscosity < 3.0 Pas at 60°C. The viscosity profile for the compound is shown in figure 5, curve II.

Recipe: 9.00 % (weight/total weight) of a styrene-ethylene/buthylene-styrene
 tri-block
 11.00 % (weight/total/weight) of oil 1
 83.00 % (weight/total weight) of oil 3

The insulating compound was prepared as the compound of example 1.

The compound had the following properties :

Dissipating factor (tgδ) at 100°C:	New compound	0.0020
	After ageing	0.0030
Dielectric strength (kV/2.5 mm) :		>40
Gas absorption (mm ³ /min) :		-7.5
Coefficient of expansion K ⁻¹ :		0.00069
Specific gravity at 20°C (g/ml) :		0.85

The results of the above examples show that the inventors have succeeded in arriving at an electrical insulating compound with good gas absorption capacities and viscosity profiles which will fulfil all the requirements mentioned above. The electrical insulating compound will absorb gas in such a way that the formation of gas bubbles (cavities) is prevented. Since the formation of cavities are prevented, there will be no sparks caused by electrical discharges, accordingly creation of electrical breakdown hazard or alteration of the dielectric will be prevented. The new insulating compound is more resistant to ageing.

The figures 1-4 shows that the viscosity is below 200 mPas at the 80°C. These insulating compounds have low viscosity at 40-80°C. This secure good impregnation of the paper wrapped cables. Since the insulating compounds can be thin liquids already at 40°C, the

production can be performed at a much higher rate than what was possible previously. The figures also shows that the viscosity to the new electrical insulating compounds are much higher below 20°C than the viscosity for the old electrical insulating compound. This give an even higher security against leakage out of the cable of the electrical insulating compound if the cable is physically damaged. In some cases a steep viscosity profile is required. This is achieved by adjusting the composition of the compound and still fulfil the other requirements. Example 4 and figure 5 show such a compound and its viscosity profile.

The new electrical insulating compounds are especially suitable for application in high voltage DC power cables as shown by the above examples. However, the compounds can also be used for other insulating purposes being obvious in view of the properties of the compounds.

Claims

1. Oil based electrical insulating compound comprising mineral oils and an oil soluble polymer being a synthetic hydrocarbonic block-copolymer of polystyrene and synthetic rubber having molecular weights from 50.000-1.000.000.
2. Oil based compound according to claim 1,
c a r a c t e r i z e d i n t h a t
the mineral oils have a content of aromates of 5-30 weight%.
3. Oil based compound according to claim 4,
c a r a c t e r i z e d i n t h a t
the rubber component of the block-copolymer is styrene-ethylene/buthylene-styrene tri-block or styrene-isoprene-styrene tri-block.
4. Oil based compound according to claim 1,
c a r a c t e r i z e d i n t h a t
the oil based compound comprises a compound which increase the gas absorption capacity.
5. Oil based compound according to claim 2,
c a r a c t e r i z e d i n t h a t
the compound which increase the gas absorption capacity is dodecylbenzene, diarylalkanes, dialkylbenzenes or alkylbenzenes.

6. Oil based compound according to claim 1,
characterized in that
the compound contains :
3 - 10 % (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block and the oil component comprises :
60 - 80 % (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons 7 - 15 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point >250°C and 7 - 15 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point >300°C.
7. Oil based compound according to claim 1,
characterized in that
the compound contains :
3-10 % (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block and the oil component comprises :
10-15 % (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons, 75-85 % (weight/total weight) of a hydrogenated, naphtenic mineral oil having boiling point >300°C.
8. Oil based compound according to claim 1,
characterized in that
the compound contains :
3-10% (weight/total weight) of a styrene-isoprene-styrene tri-block
60-70% (weight/total weight) of an mineral oil with 10-30 % aromatic and 20-30% (weight/total weight) of dodecylbenzene.

9. Oil based compound according to claim 1,
c a r a c t e r i z e d i n t h a t
the compound contains :
5.0-6.0% (weight/total weight) of a styrene-ethylene/buthylene-styrene tri-block 45-75% (weight/total weight) of an mineral oil with 10-30 % aromatic hydrocarbons and 20-50 % (weight/total weight) of a hydrogenated, naphtenic mineral oil.
10. Use of the oil based compound according to claims 1-9 as an electrical insulating and filling compound in high voltages DC power cables.

1/3




Fig. 1




Fig. 2

2/3




Fig. 3




Fig. 4

3/3




Fig. 5

INTERNATIONAL SEARCH REPORT

International application No.

PCT/NO 96/00172

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: H01B 3/20, H01B 3/22, H01B 3/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4351913 A (NAREN I. PATEL), 28 Sept 1982 (28.09.82), column 4, line 8 - line 47, claim 1, abstract ---	1-10
X	EP 0231402 A1 (SHELL OIL COMPANY ET AL), 12 August 1987 (12.08.87), claims 1-6, abstract --	1-10
A	US 3879575 A (DONALD PATRICK DOBBIN ET AL), 22 April 1975 (22.04.75) -- -----	1-10



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 October 1996

Date of mailing of the international search report

18-10-1996

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Dagmar Järvman
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/10/96

International application No.
PCT/NO 96/00172

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US-A-	4351913	28/09/82	US-A-	4324453	13/04/82
EP-A1-	0231402	12/08/87	SE-T3-	0231402	
			AU-B-	579213	17/11/88
			AU-A-	5152085	25/06/87
US-A-	3879575	22/04/75	NONE		